

# **TECHNICAL DATA SHEET**

# MAAD HYDROFIBER 15-25 ALU

#### Descripton

Thermally insulating material and sound absorber made of 100 % polyester fiber with hydrophobic properties

#### Application



20 kg/m<sup>3</sup> (±10 %)

#### TECHNICAL PARAMETERS:

 
 DENSITY

 FIRE PERFORMANCE
 EN 45545-2 ECE-R 118 Annex 6 UNI 9175 GOST 12.1.044-89 point 4.19

SOUND ABSORPTION

UNI EN 354

fulfilled the recommendations R1 – HL1, HL2, HL 3 fulfilled the recommendations fulfilled the recommendations the class 1IM index of flame spread - I=0 RANDOM INCIDENCE SOUND ABSORPTION Alpha Cabin

other available density: 15, 18, 25 kg/m<sup>3</sup>

1,0 cient 0.8 otion Coe 0,6 Absor 0,4 0,2 0.0 100 1000 10000 1800 g/m 1400 g/m<sup>2</sup> 800 g/m<sup>2</sup> 600 g/m<sup>2</sup> 3000 g/m<sup>2</sup> 20 mm 40 kg/m³ 20 mm 80 kg/m³ 30 mm 60 kg/m<sup>3</sup> 40 mm 35 kg/m³ 50 mm 60 kg/m³

Test Chamber 15,85 m<sup>3</sup>, sample 120x100 cm placed on the floor (UNI EN 354:2003). THERMAL UNI EN 12667 0,035 W/mK CONDUCTIVITY λ TEMPERATURE BS 4443/1 Met.4 - 40 and +90 °C RANGE FUNGAL ASTM G21 meets test requirements RESISTANCE **RESISTANCE FOR** HARMFUL Oeko Tex Standard 100 fulfilled the recommendations SUBSTANCES

Maad Sp. z o.o. ul. 1 Maja 21 42-217 Częstochowa NIP 949 20 39 45 tel.: +48 34 322 60 83 e-mail: biuro@maad.com.pl www.maad.com.pl





# Maad

# **TECHNICAL DATA SHEET**

HYDROPHOBIC PROPERTIES	-	water drop test > 48 h water absorption by capillary (after 48 h) < 1 mm
TENSILE STRENGHT PEAK	ASTM D3575-08 T ISO 1978	140 KPa
TENSILE ELONGATION	ASTM D3575-08 T ISO 1978	50%

### **STANDARD DIMENSIONS OF THE MATERIAL:**

THICKNESS** [mm]	DIMENSIONAL TOLERANCES [mm]	DIMENSIONS OF THE SHEET ** [mm]
10 - 80	± 1	1000 x 2000
There is a possibility of cutting to size in accordance with your spec		

\*Other thicknesses / dimensions available on customer's request. Effective dimensions guaranteed as ordered.

#### **OPTIONS\*\*\*:**

Maad HYDROFIBER ALU	without a self-adhesive layer
Maad HYDROFIBER ALU, SK-M	with a self-adhesive with a mesh layer
*** Other composites available on customer's request.	

In the case of material with adhesive layer, storage at a temperature of +15 to +30  $^\circ\mathrm{C}$ 

Maad Sp. z o.o. ul. 1 Maja 21 42-217 Częstochowa NIP 949 20 39 45 tel.: +48 34 322 60 83 e-mail: biuro@maad.com.pl www.maad.com.pl



